

No.	Characteristic	Standard As Per	Value
		ISO- 13006/EN17 6	
1	Deviation in Length & Width	±0.5%	±0.4%
2	Deviation in Thickness	±5.0%	±3.0%
3	Straightness of Sides	±0.5%	±0.5%
4	Rectangularity	±0.6%	±0.4%
5	Surface Flatness	±0.5%	±0.2%
6	Water Absorption	<5.5%	<5.5%
7	Flexural Strength	>21N/mm ²	>26N/mm ²
8	Chemical Resistance	No Damage	No Damage
9	Thermal Shock Resistance	No Damage	No Damage